United States Patent [19]

Wagener et al.

[11] 4,225,407

[45] Sep. 30, 1980

[54] CATHODIC ELECTRODEPOSITION OF POLYMERS ONTO A CONDUCTIVE SURFACE

[75] Inventors: **Earl H. Wagener**, Concord, Calif.; **Ritchie A. Wessling; Dale S. Gibbs**, both of Midland, Mich.

[73] Assignee: **The Dow Chemical Company**, Midland, Mich.

[21] Appl. No.: **26,720**

[22] Filed: **Apr. 4, 1979**

Related U.S. Application Data

[63] Continuation-in-part of Ser. No. 569,715, Apr. 21, 1975, abandoned, which is a continuation-in-part of Ser. No. 392,699, Aug. 29, 1973, abandoned.

[51] **Int. Cl.**[3] **C25D 13/06; C25D 13/10**

[52] **U.S. Cl.** ..... **204/181 C**

[58] **Field of Search** ..... 204/181 C

[56] **References Cited**

U.S. PATENT DOCUMENTS

3,455,805	7/1969	Smith et al.	204/181 C
3,567,613	3/1971	Kraus et al.	204/181 C
3,645,872	2/1972	Weigel	204/181 C

FOREIGN PATENT DOCUMENTS

1303480 1/1973 United Kingdom .

Primary Examiner—Howard S. Williams
Attorney, Agent, or Firm—I. A. Murphy

[57] **ABSTRACT**

A method for electrodeposition of an organic material on an electroconductive surface comprising placing the electroconductive surface to be coated in contact with an aqueous dispersion containing a water-insoluble, essentially electrically nonconductive, film-forming, organic polymer as cation-active particles wherein the cation-activity is provided at least predominantly by reducible nitrogen-containing cations and passing an electric current from an electrode through the latex to the electroconductive surface in such a direction that the electroconductive surface is negatively charged, i.e., becomes a cathode in an electrophoretic cell. By use of alternating current, both electrodes become coated with an adherent coating of polymer.

15 Claims, No Drawings